

**High  
density**

**High  
surface areas**

**High  
Performance  
Coconut Shell  
100%**

**Large  
micropore  
volume**

**ASTM Mesh Size 12x30**

Specifications	ACN	ASTM Method
CTC No. Min	60	ASTM D3476-04
Iodine Number, min	1200 mg/g	ASTM D4607-94
Apparent Density	0.48-0.50 g/cc	ASTM 2854-09
Abrasion No., min	85%	AWWA B 604/74
Hardness, min	95%	ASTM D3802-89
Ash, max	5%	ASTM D2866-94
Moisture as packed, max	2%	ASTM D2867-99
U.S. Standard Sieve Size	12x30	ASTM D2862-10
Larger than, max	5%	
Smaller than, max	5%	

**ASTM Mesh Size 6x12**

Specifications	ACN	ASTM Method
CTC No. Min	60	ASTM D3476-04
Iodine Number, min	1200 mg/g	ASTM D4607-94
Apparent Density	0.48-0.50 g/cc	ASTM 2854-09
Abrasion No., min	85%	AWWA B 604/74
Hardness, min	95%	ASTM D3802-89
Ash, max	5%	ASTM D2866-94
Moisture as packed, max	2%	ASTM D2867-99
U.S. Standard Sieve Size	6x12	ASTM D2862-10
Larger than, max	5%	
Smaller than, max	5%	

**ASTM Mesh Size 60x200**

Specifications	ACN	ASTM Method
CTC No. Min	60	ASTM D3476-04
Iodine Number, min	1200 mg/g	ASTM D4607-94
Apparent Density	0.48-0.50 g/cc	ASTM 2854-09
Abrasion No., min	85%	AWWA B 604/74
Hardness, min	95%	ASTM D3802-89
Ash, max	5%	ASTM D2866-94
Moisture as packed, max	2%	ASTM D2867-99
U.S. Standard Sieve Size	60x200	ASTM D2862-10
Larger than, max	5%	
Smaller than, max	5%	

**ASTM Mesh Size 50x100**

Specifications	ACN	ASTM Method
CTC No. Min	60	ASTM D3476-04
Iodine Number, min	1200 mg/g	ASTM D4607-94
Apparent Density	0.48-0.50 g/cc	ASTM 2854-09
Abrasion No., min	85%	AWWA B 604/74
Hardness, min	95%	ASTM D3802-89
Ash, max	5%	ASTM D2866-94
Moisture as packed, max	2%	ASTM D2867-99
U.S. Standard Sieve Size	50x100	ASTM D2862-10
Larger than, max	5%	
Smaller than, max	5%	

